

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 176 646 A1**

(12)

## EUROPEAN PATENT APPLICATION

(43) Date of publication:  
30.01.2002 Bulletin 2002/05

(51) Int Cl.7: H01L 51/20, H01G 9/20

(21) Application number: 00810681.7

(22) Date of filing: 28.07.2000

(84) Designated Contracting States:  
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE  
Designated Extension States:  
AL LT LV MK RO SI

(71) Applicant: ECOLE POLYTECHNIQUE FEDERALE  
DE LAUSANNE (EPFL)  
1015 Lausanne (CH)

(72) Inventors:  
• Graetzel, Michael  
1025 St-Sulpice (CH)

• Plass, Robert  
1290 Versoix (CH)  
• Bach, Udo  
Blackrock Ct. Dublin (IE)

(74) Representative: Ganguliet, Cyril et al  
ABREMA Agence Brevets & Marques Ganguliet  
& Humphrey Avenue du Théâtre 16 Case postale  
2065  
1002 Lausanne (CH)

(54) **Solid state heterojunction and solid state sensitized photovoltaic cell**

(57) A solid state p-n heterojunction comprising an electron conductor and a hole conductor; it further comprises a sensitizing semiconductor, said sensitizing semiconductor being located at an interface between

said electron conductor and said hole conductor. In particular, the sensitizing semiconductor is in form of quantum-dots. A solid state sensitized photovoltaic cell comprises such a layered heterojunction between two electrodes.

Fig. 1




Fig. 2

EP 1 176 646 A1

## Description

[0001] The present invention concerns a solid state p-n heterojunction, comprising an electron conductor and a hole conductor. The invention concerns also a solid state sensitized photovoltaic cell, in particular a solar cell.

[0002] The dye sensitized solar cells (DYSC), are more and more maturing into a technically and economically credible alternative to the conventional p-n junction photovoltaics. Photoelectrochemical (PEC) liquid junction cells based on the photosensitization of semiconductor  $\text{TiO}_2$  layers with molecular sensitizers attracted renewed interest after Graetzel et al reported energy conversion efficiencies  $>10\%$ , in Nature, 353 (1991) 737. In 1998, Graetzel et al reported in Nature, 395 (1998) 583, a more innovative all solid state cell based on a heterojunction sensitized by a molecular dye where an amorphous organic hole transport material replaced the liquid electrolyte.

[0003] The crucial part in these cells is the dye itself. Only a very limited number of dyes give high photocurrent quantum yields and are reasonably stable against photo-degradation. Some of the organic dyes exhibiting high light absorption are sensitive to air and water.

[0004] It is therefore a target of the present invention to propose photovoltaic cells having improved stability against photo-degradation and environmental influences. It is another target of the invention to achieve higher photocurrent quantum yields, higher photovoltages and hence higher conversion yields in the visible part of the light spectrum.

[0005] These aims are achieved by means of a solid state p-n heterojunction comprising a solid electron conductor, - i.e. a n type semiconductor, and a hole conductor, - i.e. a p-type semiconductor, further comprising a sensitizing semiconductor, said sensitizing semiconductor being located at the interface between the electron conductor and the hole conductor.

[0006] For the purpose of sensitization, the sensitizing semiconductor shall be light absorbing in the visible and the near infrared parts of the light spectrum, preferably up to 950 nanometers (eq to 1.4 eV).

[0007] The sensitizing semiconductor maybe provided in form of a coating film at the surface of the electron conductor. This coating film is not necessarily continuous. Only a part of the surface of the electron conductor, i.e. a part of the surfaces of the pores of a porous electron conductor may be covered by coating portions.

[0008] The sensitizing semiconductor may be provided in form of particles adsorbed at the surface of the electron conductor. The term "particles" herein refers to particles of various sizes, below a nanometer, in the nanometer range, or bigger, but excludes single discrete molecules.


[0009] A preferred kind of particles of sensitizing semiconductor for providing a solid state p-n heterojunction according to the present invention are quantum-dots.

[0010] Thereby, a preferred object of the present invention is a new embodiment of a sensitized solar cell where the molecular sensitizer is replaced by a small semiconductor particle, referred to in scientific papers as "nano-dot" or "quantum dot" or "Q-dot". Quantum dots are semiconductor particles of nanometer size wherein a gradual translation from solid state to molecular structure occurs as the particles size decreases. The quantum dots are adsorbed at the heterojunction constituted by a n-type semiconductor and a p-type semiconductor.

[0011] Preferably, the n-type semiconductor is a finely divided and sintered large band gap ceramic oxide. Various metal oxides like  $\text{Ta}_2\text{O}_5$ ,  $\text{Nb}_2\text{O}_5$ ,  $\text{SnO}_2$ ,  $\text{ZnO}$  may be used as solid electronic conductors, whereas nanocrystalline  $\text{TiO}_2$  (anatase) is preferred.

[0012] The hole conductor may be selected from hole transporting inorganic solids like copper iodide or copper thiocyanate. Typically, the hole conductor may be an organic charge transport material. This organic charge transport material may be a polymer, like poly-tiophen or a poly-arylamine. The hole conductor of the present invention may also be an amorphous, reversibly oxidizable organic non-polymeric compound.

[0013] As such a compound, The hole conductor may be selected from the group consisting of spiro- and hetero spiro compounds of general formula (I)



[0014] Wherein  $\phi$  is one of C, Si, Ge or Sn and K1 and K2 are, independently one of the other, conjugated systems.

A particularly preferred hole conductor is 2,2',7,7'-tetrakis (N,N-di-p-methoxyphenyl-amine)9,9'-spirobifluorene, herein further called OMeTAD.

[0015] As quantum dots, particles consisting of CdS, Bi<sub>2</sub>S<sub>3</sub>, Sb<sub>2</sub>S<sub>3</sub> or Ag<sub>2</sub>S may be used, whereas PbS is preferred. Other compounds suitable for making quantum-dots are In As, CdTe, CdSe, HgTe. Solid solutions of HgTe and CdTe or of HgSe and CdSe are also suitable.

[0016] A preferred quantum dot sensitized nanocrystalline heterojunction is constituted of sintered particles of nanocrystalline TiO<sub>2</sub> onto which PbS particles in the nanometer range are absorbed as sensitizers, the pores between the particles being filled with amorphous OMeTAD.

[0017] The mesoscopic nature of the heterojunction results in a high contact area of the junction, which is a prerequisite for efficient solar light harvesting by the quantum dots. Light is adsorbed by the Q-dots and produces electron-hole pairs. The electrons are injected from the Q-dots into the electron conducting solid while the holes are injected in the hole conducting side of the junction. In this way electric power is produced from light.

[0018] While the sensitization of oxide semiconductors by Q-dots has already been reported for liquid junction cells by Vogel et al, in Chem. Phys. Lett., 174 (1990) 241, these devices show notorious problems with corrosion and photo-corrosion of the Q-dots by the electrolyte rendering them unsuitable for practical applications. Also the Q-dots tended to aggregate at the solid-liquid junction rendering them unsuitable for sensitization. The present invention realises a solid state heterojunction cell that does not present these disadvantages and hence can be used for the conversion of sunlight to electric power.

[0019] Quantum dot sensitized heterojunction cells offer several advantages. The band gaps and thereby the absorption ranges are adjustable through the particle size or by adjusting the relative concentrations of components in solid solutions like HgTe/CdTe or HgSe/CdSe. The band gap of these solutions may be adjusted to approach the optimal value for conversion of sunlight to electric power, which is about 1.4-1.5 eV.

[0020] Furthermore, compared to organic dyes, quantum dot sensitization offers improved stability, since the surface of the Q-dots can be modified to improve their photostability. Another advantage is that the optical cross section of the Q-dots is significantly larger than the one of the molecular dyes. This allows to employ thinner films resulting in higher photovoltages as well as better fill factors of the cell, and hence higher conversion yields. Whereas only a limited number of molecular dyes suit the requirements of DYSC, Q-dot semiconductors have very high extinction coefficients and hence are very effective sensitizers. Since photo generated e<sup>-</sup> and h<sup>+</sup> can be separated effectively as in n-p junctions, quantum dot sensitization offers a means to combine the mechanical features, efficiency and weather-ruggedness of single crystalline or polycrystalline p-n photovoltaics with an excellent spectral range coverage.

[0021] Other features and advantages of the present invention will appear to those skilled in the art from the following description of an embodiment of a solid state sensitized photovoltaic cell, from the description of a process for making a solid state heterojunction and from measurements made with such a cell in conjunction with the drawings, among which :

- figure 1 shows a schematic view of a solid state sensitized photovoltaic cell;
- figure 2 is an enlarged view of a heterojunction within the nanocrystalline TiO<sub>2</sub> layer;
- figure 3 shows absorption spectra of TiO<sub>2</sub> plates with different deposition treatments; and
- figure 4 shows the photo current generation efficiency as a function of wavelength for Q-dot sensitized solid state heterojunction solar cells.

[0022] Figure 1 shows the schematic build up of a solid state sensitized photovoltaic cell. From bottom to top there are :

- an ITO transparent glass support 1;
- the glass support 1 is coated by a transparent conducting layer 2 made of F doped SnO<sub>2</sub>, thereby the coated glass acts as a working electrode, which collects charge and current.
- a dense TiO<sub>2</sub> layer 3 for avoiding direct contact between the organic hole conductor and the SnO<sub>2</sub>, which would short circuit the cell;
- a quantum dot sensitized nanocrystalline layer 4, forming a heterojunction, which is build up as will be explained below;
- the back contact 5 of the cell is made of a fine gold layer of 10 nanometers covered by a thick nickel layer for a better current collection.

[0023] Figure 2 shows a magnified schematic view of the microscopic structure of the layered heterojunction : at the

surface of  $\text{TiO}_2$  particles 6, are adsorbed Q-dots 7; the spaces are filled with particles 8 of an organic hole conductor.

Example : process for making a layered heterojunction

- 5 [0024] The compact  $\text{TiO}_2$  layer is deposited on the  $\text{SnO}_2$ -coated glass by spray pyrolysis. This process is performed following the procedure described in the thesis No. 2187 at EPFL of Udo Bach. The nanoporous  $\text{TiO}_2$  layer is deposited by screen printing. The plates are thereafter sintered at a temperature of  $450^\circ\text{C}$  for 15 min. This results in a layer with a thickness of about  $2\text{ }\mu\text{m}$ . The plates are thereafter stored in water free atmosphere.
- 10 [0025] The technique used to deposit the Q-dots follows the procedure published by Weller et al in J. Phys. Chem. 98, 1994, 3183. Two solutions are needed for this technique, the first one is a saturated  $\text{Pb}(\text{NO}_3)_2$  solution in water, and the second one a  $0.3\text{M}$   $\text{Na}_2\text{S}$  solution in water. The plates are immersed for 1 minute in the first solution. Thereafter, they are rinsed with water and dipped into the second solution for about 10 sec and then rinsed again. This deposition procedure may be repeated several times.
- 15 [0026] After the deposition of the Q-dots, the hole-conductor is introduced into the pores of the nanocrystalline structure by spin-coating. The spin-coating solution is a 30% by weight solution of OMeTAD in chlorobenzene. The OMeTAD may be doped with 0.2% of OMeTAD $^+$ . An amount of  $150\text{ }\mu\text{l}$  of spin-coating solution is used for each plate. Subsequently, the solvent is evaporated.
- [0027] A semi-transparent gold back contact is evaporated on top of the heterojunction layer under vacuum. A second contact layer made of nickel is sprayed onto the first one.
- 20 [0028] Absorption spectra are measured with a Hewlett-Packard 8453 spectrometer and are shown in Figure 3. Figure 3 shows that repeating the Q-dot deposition treatment results in an increase of the visible absorption of the electrode. With each deposition, the optical density increases and the electrode becomes strongly coloured. The Q-dots are getting bigger with each treatment.
- 25 [0029] Figure 4 shows the wavelength response of the photocurrent produced by the device. The incident photon to current conversion efficiency (IPCE) is plotted as a function of the wavelength of the monochromatic light. The conversion yields are high, exceeding 10 percent in the visible. This proves that the sensitization of the heterojunction by the quantum dots functions well.
- [0030] From these measurements, it can be seen that there is an optimum in the number of times the deposition treatment is repeated. For this embodiment, if only one treatment is done, there is not enough Q-dots formed on the
- 30  $\text{TiO}_2$  surface. On the other hand, if there are too many deposition treatments, typically 10, as shown in figure 4, the Q-dots get too big and the efficiency drops.

#### Claims


- 35 1. A solid state p-n heterojunction comprising an electron conductor and a hole conductor, **characterised in that** it further comprises a sensitizing semiconductor, said sensitizing semiconductor being located at an interface between said electron conductor and said hole conductor.
- 40 2. A heterojunction as claimed in claim 1, wherein said sensitizing semiconductor is in form of a coating film at the surface of said electron conductor.
- 45 3. A heterojunction as claimed in claim 1, **characterised in that** said sensitizing semiconductor is form of particles adsorbed at the surface of said electron conductor.
- 50 4. A heterojunction as claimed in claim 3, **characterised in that** said sensitizing semiconductor is in form of quantum-dots.
5. A heterojunction as claimed in anyone of claims 1-4, **characterised in that** said electron conductor is an n-type semiconductor and said hole conductor is a p-type semiconductor.
6. A heterojunction as claimed in claim 5, **characterised in that** said n-type semiconductor is a ceramic made of a finely divided large band gap metal oxide.
- 55 7. A heterojunction as claimed in anyone of claims 1-6, **characterised in that** said electron conductor is nanocrystalline  $\text{TiO}_2$ .
8. A heterojunction as claimed in anyone of claims 1-7, **characterised in that** said hole conductor is an inorganic

hole transporting solid compound.

9. A heterojunction as claimed in anyone of claims 1-6, **characterised in that** said hole conductor is an amorphous reversibly oxydisable organic compound.

10. A heterojunction as claimed in claim 9, **characterised in that** said organic compound is a polymer.

11. A heterojunction as claimed in anyone of claims 1-7 or 9, **characterised in that** said hole conductor is selected from the group consisting of Spiro and Heterospirocompounds of general formula (I),



wherein 4 is one of C, Si, Ge or Sn, and K1 and K2 are independently one from the other conjugated systems.

12. A heterojunction as claimed in claim 11, wherein said hole conductor is OMeTAD.

13. A heterojunction as claimed in anyone of claims 4-12, wherein said quantum dots are particles consisting of PbS, CdS, Bi<sub>2</sub>S<sub>3</sub>, Sb<sub>2</sub>S<sub>3</sub>, Ag<sub>2</sub>S, InAs, CdTe, CdSe or HgTe or solid solutions of HgTe/CdTe or HgSe/CdSe.

14. A solid state sensitized photovoltaic cell comprising a layered heterojunction as claimed in anyone of claims 1-13.

15. A cell as claimed in claim 14, **characterised in that** it comprises

- a transparent first electrode,
- a said layered heterojunction and
- a second electrode.

16. A cell as claimed in claim 15, further comprising a dense semiconductive layer between said first electrode and said layered heterojunction.

17. A cell as claimed in anyone of claims 14-16, **characterised in that** said layered heterojunction is obtained by forming quantum dots on the surface of said electron conductor by at least one deposition treatment, before providing said hole conductor to said layered heterojunction.

18. A cell as claimed in claim 17, **characterised in that** said deposition treatment is performed 2-10 times before providing said hole conductor.



Fig. 1




Fig. 2





Fig. 3



-- Treated 1x (Integrated current from 340 to 800 is  $1.4 \text{ mA/cm}^2$ )  
 — Treated 5x (Integrated current from 340 to 800 is  $2.0 \text{ mA/cm}^2$ )  
 ..... Treated 10x (Integrated current from 340 to 800 is  $1.1 \text{ mA/cm}^2$ )

**Fig. 4**





European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 00 81 0681

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	C ROST ET AL: "Transparent p-type semiconductors for the ETA solar cell with Extremely Thin Absorber" 2ND WORLD CONFERENCE AND EXHIBITION ON PHOTOVOLTAIC SOLAR ENERGY CONVERSION, 6 - 10 July 1998, pages 212-215, XP002141360 VIENNA, AT * the whole document *	1,2,5-7, 14,15	H01L51/20 H01G9/20
Y		1,3-7, 15-18	
X	S. SIEBENTRITT ET AL.: "CdTe and CdS as extremely thin absorber materials in an eta solar cell" 14TH EUROPEAN PHOTOVOLTAIC SOLAR ENERGY CONFERENCE, 30 June 1997 (1997-06-30) - 4 July 1997 (1997-07-04), pages 1823-1826, XP002156223 BARCELONA, ES * the whole document *	1-3,5-7, 14,15	
Y,D	VOGEL R ET AL: "SENSITIZATION OF HIGHLY POROUS, POLYCRYSTALLINE TiO2 ELECTRODES BY QUANTUM SIZED CDS" CHEMICAL PHYSICS LETTERS,AMSTERDAM,NL, vol. 174, no. 3/04, 9 November 1990 (1990-11-09), pages 241-246, XP000956095 * the whole document *	1,3-7, 13-18	H01L H01G
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>21 December 2000</b>	Examiner <b>Visentin, A</b>
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04001)



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 00 81 0681

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A, D	VOGEL R ET AL: "QUANTUM-SIZED PBS, CDS, AG2S, AND BI2S3 PARTICLES AS SENSITIZERS FOR VARIOUS NANOPOROUS WIDE-BANDGAP SEMICONDUCTORS" JOURNAL OF PHYSICAL CHEMISTRY, AMERICAN CHEMICAL SOCIETY, US, vol. 98, no. 12, 1994, pages 3183-3188, XP000956096 ISSN: 0022-3654 * the whole document *	1, 3-7, 13-18	
A	SALAFSKY J S ET AL: "PHOTOINDUCED CHARGE SEPARATION AND RECOMBINATION IN A CONJUGATED POLYMER-SEMICONDUCTOR NANOCRYSTAL COMPOSITE" CHEMICAL PHYSICS LETTERS, AMSTERDAM, NL, vol. 290, no. 4/06, 3 July 1998 (1998-07-03), pages 297-303, XP000884003 * the whole document *	1, 5-7, 10, 14, 15	
A	GREENHAM N C ET AL: "CHARGE SEPARATION AND TRANSPORT IN CONJUGATED-POLYMER/SEMICONDUCTOR-NANOCRYSTAL COMPOSITES STUDIED BY PHOTOLUMINESCENCE QUENCHING AND PHOTOCONDUCTIVITY" PHYSICAL REVIEW, B. CONDENSED MATTER, US, AMERICAN INSTITUTE OF PHYSICS, NEW YORK, vol. 54, no. 24, 15 December 1996 (1996-12-15), pages 17628-17637, XP002060964 ISSN: 0163-1829 * the whole document *	1, 3, 4, 10, 13-15	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 21 December 2000	Examiner Visentin, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on or after the filing date D: document cited in the application L: document cited for other reasons &amp;: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04C01)



European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 00 81 0681

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	BACH U ET AL: "SOLID-STATE DYE-SENSITIZED MESOPOROUS TiO <sub>2</sub> SOLAR CELLS WITH HIGH PHOTON-TO-ELECTRON CONVERSION EFFICIENCIES" NATURE, GB, MACMILLAN JOURNALS LTD. LONDON, vol. 395, 8 October 1998 (1998-10-08), pages 583-585, XP000783901 ISSN: 0028-0836 * the whole document *	1,5-7, 11,12, 14,15	
A	MOELLER J ET AL: "A NOVEL DEPOSITION - TECHNIQUE FOR COMPOUND SEMICONDUCTORS ON HIGHLY POROUS SUBSTRATES: ILGAR" THIN SOLID FILMS, ELSEVIER-SEQUOIA S.A. LAUSANNE, CH, vol. 361/362, 21 February 2000 (2000-02-21), pages 113-117, XP000922979 ISSN: 0040-6090	-	
A	DE 197 11 713 A (HOECHST AG) 1 October 1998 (1998-10-01)		
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 21 December 2000	Examiner Visentin, A
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &amp;: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 B2 (P04C01)

EP 1 176 646 A1

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 81 0681

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

21-12-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 19711713 A	01-10-1998	WO 9848433 A	29-10-1998
		EP 0968507 A	05-01-2000

EPO FORM P0458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82